

LAPONITE-XLG XR

Synthetic Layered Silicate Thickener for Water Phases in Cosmetic Applications

Product Data

INCI Name

Lithium Magnesium Sodium Silicate (nano)

Product Description

LAPONITE-XLG XR is a synthetic layered silicate with low heavy metal content. It is insoluble in water but hydrates and swells to give clear and colorless colloidal dispersions in water or aqueous solutions of alcohols. At concentrations of 2 % or greater in water, highly thixotropic gels are obtained. The unique shear thinning and thixotropic rheology of LAPONITE-XLG XR improves the skin feel of personal care products. Formulations will have a light, non-sticky texture. LAPONITE-XLG XR enhances stability of formulations and keeps particles, pigments or solid actives suspended; it is a very effective agent for stabilizing surfactant-free o/w emulsions. LAPONITE-XLG XR has been sterilized by gamma irradiation.

Typical Properties

The values indicated in this data sheet are typical and do not constitute specification limits.

Appearance:	Free flowing, white powder
Opacity:	Pass
Surface Area (BET):	370 m ² /g
Loose Bulk Density:	1000 kg/m ³
pH Value (2 % dispersion in water):	report value
Moisture:	max. 10.0 %
Sieve Analysis + 250 µm:	max. 2 %
Gel Strength:	min. 22 g
Gel Time:	max. 6 min
Dispersion Rate:	max. 25
Clarity:	max. 15
Lead (as Pb):	max. 5 mg/kg
Arsenic (as As):	max. 1 mg/kg
Bacteria Count:	max. 10 cfu/g

Recommended Use

Used for imparting a shear sensitive structure to a wide range of personal care products.

Application areas:	Personal Care:	Cream and Lotion Sunscreen Product Depilatory Cream Toothpaste Bath and Shower Gel Anti-dandruff Shampoo
	Color Cosmetics:	Liquid Make-up Foundation Liquid Eyeliner

LAPONITE-XLG XR

Data Sheet
Issue 05/2018

Incorporation and Processing Instructions

Recommended laboratory mixing equipment is a mechanical stirrer fitted with a propeller blade.

Add LAPONITE-XLG XR to deionized water (at 15 – 25 °C) in a steady stream over 10 - 30 seconds with rapid agitation. Mixer speed should be high enough to produce a vortex that will cause the stream of LAPONITE powder to wet out into the water without the formation of clumps. Mixing should be continued for up to 20 minutes. When dispersion is complete, LAPONITE-XLG XR produces a clear, colorless and low viscosity pre-mix.

Viscosity development will occur instantaneously when the pre-mix is combined with other formulation components. Note that the viscosity of the LAPONITE-XLG XR pre-mix can be affected by temperature, electrolytes or pH level. Recommended agents are citric acid, lactic acid or sodium dihydrogen phosphate.

It can be difficult to disperse very strong gels of LAPONITE-XLG XR homogeneously into formulations without formation of gel-seeds. If there is not enough free water available to avoid this, the pre-gel may be “de-gelled” by addition of compounds such as tetrasodium pyrophosphate or low molecular weight glycols e.g. PEG and PPG. This de-gelling effect is overcome on addition of the pre-mix to a formulation.

Recommended Levels

Use levels in a formulation are highly dependent upon the composition of the formulation and can range from 0.1% up to 5%. LAPONITE products are very commonly used in synergistic combinations with polymeric co-thickeners, including xanthan gum, CMC, HASE, etc. These combinations will often allow the formulator to reduce total thickener levels required to produce a stable product.

These levels are suggested as a guideline; optimum levels can be determined by laboratory tests.

Special Note

LAPONITE-XLG XR is not compatible with cationic compounds. Recommended agents to lower formulation pH are citric acid, lactic acid or sodium dihydrogen phosphate to increase the formulation pH, sodium hydroxide can be used. LAPONITE-XLG XR is a weak base and will often cause formulation pH to rise to >6.5 within 24 hours. This effect can be overcome by making the initial pH adjustment to a value below the target equilibrium pH level of the finished product.

LAPONITE-XLG XR is compatible with up to 40% ethanol solution. In synergistic combinations with co-thickeners, LAPONITE-XLG XR can be used in formulations containing >60% ethanol.

Storage and Transportation

LAPONITE-XLG XR is hygroscopic and should be stored under dry conditions, in original packaging.

BYK-Chemie GmbH
P.O. Box 10 02 45
46462 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com/additives

ACTAL®, ADJUST-4®, ADVITROL®, BENTOLITE®, CLAYTONE®, CLOISITE®, COPISIL®, FULACOLOR®, FULCAT®, FULGEL®, FULMONT®, GARAMITE®, GELWHITE®, LAPONITE®, MINERAL COLLOID®, OPTIBENT®, OPTIFLO®, OPTIGEL®, PERMONT®, PURE THIX®, RHEOCIN®, RHEOTIX®, RIC-SYN®, SCP®, TIXOGEL®, Y25® are registered trademarks of BYK Additives.

ANTI-TERRA®, BYK®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKETOL®, BYKJET®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, DISPERBYK®, DISPERPLAST®, LACTIMON®, NANOBYPK®, PAPERBYK®, SILBYK®, VISCOBYK®, and Greenability® are registered trademarks of BYK-Chemie. AQUACER®, AQUAMAT®, AQUATIX®, CERACOL®, CERAFAX®, CERAFLOUR®, CERAMAT®, CERATIX®, HORDAMER®, and MINERPOL® are registered trademarks of BYK-Cera.

SCONA® is a registered trademark of BYK Kometra.

This information is given to the best of our knowledge. Because of the multitude of formulations, production, and application conditions, all the above-mentioned statements have to be adjusted to the circumstances of the processor. No liabilities, including those for patent rights, can be derived from this fact for individual cases.

This issue replaces all previous versions – Printed in Germany